OXIDE SUPERCONDUCTING WIRE

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001]   The present invention relates to an oxide superconducting wire, and more particularly relates to an oxide superconducting wire having an intermediate layer between a substrate and an oxide superconducting film.

2. Description of the Prior Art

[0002]   RE-123-based oxide superconductors ($REBa_2Cu_3O_{7-x}$; RE is a rare earth element including yttrium) are considered materials with extremely promising practical applications because they exhibit superconductivity over the temperature of liquid nitrogen, and there has been a great need for some way to work these materials into a wire for use as a conductor in power supply applications.

[0003]   One method that has been studied for working an oxide superconductor into a wire is to produce a thin tape from a metal that has high strength and good heat resistance and lends itself to working into a wire, and form an oxide superconducting thin film on this metal tape substrate.

[0004]   An oxide superconductor has electrical anisotropy, wherein the crystals themselves readily conduct electric current in the a and b axial directions of the crystal axis, but not so well in the c axial direction. Therefore, when an oxide superconductor is formed on a substrate, the a axis or b axis must be oriented in the direction in which electric current flows, and the c axis oriented in vertically to the flat surface.

[0005]   However, the metal tape substrate itself is either
amorphous or polycrystalline, and the crystal structure
thereof differs greatly from that of an oxide
superconductor, so it is difficult to form an oxide
superconducting film having the above-mentioned good
crystal orientation on this substrate. Also, the thermal
expansion coefficient and the lattice constant of the
substrate are different from those of the superconductor,
which can result in strain being produced in the
superconductor or in the oxide superconducting film
separating from the substrate, in the course of cooling
down to the superconducting critical temperature.

[0006]   In view of this, what has been done to solve the
above problems is to first form an intermediate
layer(buffer layer), composed of a material such as MgO,
YSZ (yttria stabilized zirconium), or $SrTiO_3$ whose physical
properties such as thermal expansion coefficient and
lattice constant are midway between those of the substrate
and those of the superconductor, on a metal tape substrate,
and then form an oxide superconducting film on this
intermediate layer.

[0007]   Nevertheless, even when an intermediate layer is
formed as above, the resulting oxide superconducting film
has such a low critical current density as to be
impractical. The reason for this is that the oxide
superconducting film is obtained in a state in which
numerous single-crystal grains are bonded in the planar
direction of the substrate, forming a polycrystalline film,
and the c axis of the individual crystal grains is oriented
perpendicular to the substrate surface, but the a and b
axes are still randomly oriented as shown in Fig. 1A, so
crystal orientation is poor.

[0008]   In view of this, a method for improving crystal
orientation has been proposed (see Japanese Patent No.

2,721,595). This method is generally referred to as an
IBAD (Ion Beam Assisted Deposition) method, the basics of
which are illustrated in Fig. 2.

[0009]   As shown in Fig. 2, a metal substrate 1 on which a
superconducting thin film is to be formed, a target 2
disposed opposite and at an angle to this metal substrate 1,
a sputtering beam emitter 3 for sputtering the particles
that make up the target 2, and an ion source 4 for
obliquely directing ions of a rare gas at the surface of
the substrate, are disposed within a vacuum vessel.

[0010]   The inside of the vessel is evacuated to create a
reduced pressure atmosphere, and the ion source 4 and the
sputtering beam emitter 3 are actuated. Ions are emitted
from the sputtering beam emitter 3 and directed at the
target 2, which sputters the particles that make up the
target 2 and deposits them on the metal substrate 1, and at
the same time, mixed ions comprising rare gas ions and
oxygen ions are emitted from the ion source 4 and directed
at a specific irradiation angle (θ) at the substrate
surface.

[0011]   Thus sputtering while performing ion irradiation
at a specific irradiation angle allows the a and b axes of
the crystals in the polycrystalline thin film of the
intermediate layer to be oriented.

[0012]   When an oxide superconducting film is formed by
sputtering or laser deposition on an intermediate layer
formed as above, the resulting superconducting film is also
deposited so as to match the crystal orientation of the
intermediate layer, and the crystals of the superconducting
film grow in this fashion, so critical current density is
large. This state is shown in Fig. 1B.

[0013]   However, for example, when $YBa_2Cu_3O_{7-y}$ (hereinafter
also referred to as YBCO) is formed on a YSZ layer formed
by the IBAD method as above, barium diffuses from the YBCO

layer into the YSZ layer, forming BaZrO₃ on the YSZ layer, which is a problem in that it decreases the critical temperature (Tc) and the critical current density (Jc).

[0014]   As one method for manufacturing an oxide superconducting film at low cost, there is mentioned a method (TFA-MOD method) in which a solution containing a stoichiometric amount of a trifluoroacetate (TFA) of the metal elements constituting an oxide superconductor is applied onto a substrate surface, and pyrolyzed to create an oxide superconducting film. However, when a YBCO film is formed on a YSZ layer by this method, hydrogen fluoride gas is produced in the course of the heating and decomposition, and this gas reacts with the YSZ, which prevents good superconducting characteristics from being obtained.

[0015]   A method that has been proposed for solving the above problems involves forming a layer of CeO_2, which is a compound that suppresses the diffusion of barium into the YBCO layer or YSZ layer or the reaction between YSZ and hydrogen fluoride, and which also has a thermal expansion coefficient close to that of YBCO and low reactivity with YBCO, and then forming a YBCO film on this layer. In the present Specification this CeO_2 layer is referred to as a cap layer to distinguish it from the intermediate layer. The following are examples of providing this cap layer.

[0016]   It is stated in IEEE Transactions on Applied Superconductivity, Vol. 11, No. 1 (March 2001), 2927-2930, that a CeO_2/YSZ/CeO_2/Ni substrate is coated with a solution of a YBCO precursor composed of a metal trifluoroacetate, after which the solution is pyrolyzed, which yields a YBCO film, and the thickness of the CeO_2 film is described to be 20 nm.

[0017]   It is described in IEEE Transactions on Applied Superconductivity, Vol. 11, No. 1 (March 2001), 3489-3492, that polycrystalline yttrium-iron/garnet (YIG) is used as a

substrate, and while no mention of superconducting wire is made, it is said that a buffer layer composed of two layers, namely, a YSZ layer formed by the IBAD method and a CeO_2 layer formed by a pulsed laser deposition method (hereinafter, referred to as "PLD method"), is formed on the YIG substrate, and a YBCO film is formed on this buffer layer, and that the thickness of the YSZ layer is 800 ±100 nm, and the thickness of the CeO_2 layer is about 20 nm.

[0018]   It is described in J. Mater. Res., Vol. 15, No. 5 (May 2000) that a YSZ layer is formed by the IBAD method on a nickel alloy substrate, and then a CeO_2 layer and a YBCO layer are formed by the PLD method on this, and that the thickness of the CeO_2 layer is 30 nm and the thickness of the YSZ layer is 800 nm.

[0019]   It is described in IEEE Transactions on Applied Superconductivity, Vol. 11, No. 1 (March 2001), 3359-3364 that a YSZ layer is formed on a nickel alloy substrate by the IBAD method, and first a CeO_2 layer and then a YBCO layer are formed by the PLD method on this, and that the thickness of the YSZ layer is 500 nm and the thickness of the CeO_2 layer is 30 nm.

[0020]   It is described in Physica C 357-360 (2001), 1003-1006 that a YSZ layer is formed on a Hastelloy tape substrate by the IBAD method, a CeO_2 layer is formed by the PLD method on this, and then a YBCO film is formed by the TFA-MOD method, and that the thickness of the CeO_2 layer is 100 to 2000 nm. (There is no mention of the thickness of the YSZ layer, however.)

[0021]   Unfortunately, the IBAD method used to form this intermediate layer has the drawback of slow film formation. Further, if a YSZ layer is deposited on a substrate by the IBAD method, the orientation of the film will be inadequate if the film is thin, and the film thickness has to be about 1000 nm for the desired orientation to be achieved. Also,

obtaining a film 1000 nm in thickness by the IBAD method takes considerable time, which is a problem in terms of productivity.

SUMMARY OF THE INVENTION

[0022]   It is an object of the present invention to shorten the time required by the IBAD method to manufacture a superconducting wire composed of a substrate, an intermediate layer, a cap layer, and an oxide superconducting film, and thereby increase the productivity of superconducting wire.

[0023]   It is a further object of the present invention to increase the critical current density of an oxide superconducting wire by decreasing the surface roughness and increasing the orientation of the cap layer where the oxide superconducting film is formed.

[0024]   As a result of diligent research aimed at solving the above problems, the inventors achieved the present invention upon discovering that when a CeO_2 layer is provided as a cap layer on an intermediate layer formed by the IBAD method, even if the intermediate layer is made thinner, as long as the cap layer is made thicker, a superconducting film with good orientation will be obtained.

[0025]   Specifically, the specific constitution of the present invention for solving the stated problems is as follows.

[0026]   (1) An oxide superconducting wire composed of a metal substrate, an intermediate layer vapor-deposited by an ion beam assisted deposition method (IBAD method) on the metal substrate, a CeO_2 cap layer vapor-deposited on the intermediate layer, and an oxide superconducting film formed on the cap layer, wherein the thickness of the

intermediate layer is no more than 2000 nm, and the thickness of the cap layer is at least 50 nm.

[0027]   (2) The oxide superconducting wire according to (1) above, wherein the oxide superconducting film is composed of an RE-123-based oxide superconductor ($REBa_2Cu_3O_{7-x}$; RE is a rare earth element including yttrium).

[0028]   (3) The oxide superconducting wire according to (1) or (2) above, wherein the intermediate layer is composed of a material selected from the group consisting of $Gd_2Zr_2O_7$, YSZ (yttria stabilized zirconium), and MgO.

[0029]   (4) The oxide superconducting wire according to any of (1) to (3) above, wherein the thickness of the intermediate layer is at least 10 nm.

[0030]   (5) The oxide superconducting wire according to any of (1) to (4) above, wherein the orientation ($\Delta\Phi$) of the intermediate layer is at least 10 degrees.

[0031]   (6) The oxide superconducting wire according to any of (1) to (5) above, wherein the orientation ($\Delta\Phi$) of the cap layer is better than the orientation ($\Delta\Phi$) of the intermediate layer.

[0032]   (7) The oxide superconducting wire according to any of (1) to (6) above, wherein the thickness of the cap layer is no more than 5000 nm.

[0033]   (8) The oxide superconducting wire according to any of (1) to (7) above, wherein the orientation ($\Delta\Phi$) of the cap layer is no more than 10 degrees.

[0034]   (9) The oxide superconducting wire according to any of (1) to (8) above, wherein the cap layer is formed by a pulsed laser deposition method (PLD method).

[0035]   (10) The oxide superconducting wire according to any of (1) to (9) above, wherein the cap layer is formed at a rate higher than a rate at which the intermediate layer is formed.

[0036]   (11) The oxide superconducting wire according to any of (1) to (10) above, wherein the cap layer is formed at a rate of 1 to 5000 nm/min.

[0037]   (12) The oxide superconducting wire according to any of (1) to (11) above, wherein the cap layer is formed at a PLD laser energy density of 1 to 5 J/cm^2.

[0038]   (13) The oxide superconducting wire according to any of (1) to (12) above, wherein the oxide superconducting film is a Y123 phase, Sm123 phase, or Nd123 phase.

[0039]   (14) The oxide superconducting wire according to any of (1) to (13) above, wherein the oxide superconducting film is formed by a pulsed laser deposition method (PLD method) or a metal organic deposition method (MOD method).

[0040]   (15) The oxide superconducting wire according to any of (1) to (14) above, wherein the metal substrate is composed of a material selected from the group consisting of Hastelloy, stainless steel, nickel alloys, silver, and silver alloys.

BRIEF DESCRIPTION OF THE DRAWINGS

[0041]   Fig. 1A shows how the a axis of the individual crystal grains constituting an oxide superconducting film is not oriented, and Fig. 1B shows the a axis of the individual crystal grains is oriented.

[0042]   Fig. 2 is a simplified diagram of the film formation process by the IBAD method.

[0043]   Fig. 3 is an illustration showing the layer structure of the superconducting wire of the present invention.

[0044]   Fig. 4 is a graph showing the relationship of $\Delta\Phi$ to the film thickness of $Gd_2Zr_2O_7$ and YSZ, and the film formation rate.

[0045]   Fig. 5 is a graph showing the relationship of IBAD film thickness to the $\Delta\Phi$ of the CeO_2 layer formed thereon.

[0046]   Fig. 6 is a graph showing the relationship of IBAD film thickness to the critical current density of the resulting superconducting film.

[0047]   Fig. 7 is a graph showing the $\Delta\Phi$ of the CeO_2 film versus the thickness of the CeO_2 film.

[0048]   Fig. 8 is a graph showing the CeO_2 film formation rate versus the surface roughness (Ra) of the resulting CeO_2 layer.

[0049]   Fig. 9 is a graph showing the laser energy density versus the crystal orientation $\Delta\Phi$ of the resulting CeO_2 layer.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0050]   Embodiments of the present invention will now be described.

[0051]   The superconducting wire of the present invention has the layer structure shown in Fig. 3, consisting of an oxide superconducting film, a cap layer (CeO_2 layer), an IBAD intermediate layer, and a metal substrate.

[0052]   The materials used to form each of these layer will now be discussed.

<Substrate Material>

[0053]   Copper, nickel, titanium, molybdenum, niobium, tantalum, tungsten, manganese, iron, silver, and other such metals and alloys thereof that offer excellent strength and heat resistance can be used as the metal substrate used in the oxide superconducting wire of the present invention. Stainless steel, Hastelloy, and other nickel alloys are particularly favorable because of their superior resistance to corrosion and heat.

<Intermediate layer>

[Material]

[0054] The intermediate layer is formed by the IBAD method. Examples of the material used to form this intermediate layer include YSZ, MgO, $SrTiO_3$, and $Gd_2Zr_2O_7$, and it is also possible to use any suitable compound having a pyrochlore structure, rare earth-C structure, perovskite structure, or fluorite structure. Of these, the use of YSZ or $Gd_2Zr_2O_7$ is preferable. $Gd_2Zr_2O_7$ is a particularly suitable intermediate layer material because not only is its IBAD film formation rate higher than that of YSZ, but its $\Delta\Phi$ (FWHM: full width at half maximum), which is an index of orientation, is also smaller. Fig. 4 shows the relationship of $\Delta\Phi$ to film thickness when films were made from $Gd_2Zr_2O_7$ and from YSZ. This graph indicates that $Gd_2Zr_2O_7$ has a higher orientation rate and a smaller $\Delta\Phi$ than YSZ.

[Film Thickness]

[0055] It has been said in the past that an intermediate layer formed by the IBAD method (hereinafter also referred to as an IBAD film) will not afford good orientation unless it is about 1000 nm thick. The deposition rate by the IBAD method, however, is only about 3 nm/minute, which poses a problem in terms of productivity.

[0056] However, if a CeO_2 layer is formed in at least a certain thickness on an IBAD layer, even if the thickness of the IBAD film is no more than 1000 nm, the resulting CeO_2 layer will have good orientation, and when an oxide superconducting film is formed on this CeO_2 layer, this oxide superconducting film will exhibit high critical current density. This CeO_2 layer can be formed by the PLD method, and since the PLD method allows a film to be formed at high speed (5000 nm/minute, for example), even if the IBAD film is made thin and the CeO_2 layer is made thick,

there will be a significant increase in the total film
formation rate, which affords better productivity.

[0057]   For the above reasons, the thickness of the
intermediate layer in the present invention should be no
more than 1000 nm.   1000 nm may be exceeded, but since it
takes a long time to form a film by the IBAD method as
mentioned above, a film thickness over 1000 nm is
undesirable in terms of productivity.   Furthermore,
exceeding 2000 nm is undesirable because surface roughness
will be larger and there will be a decrease in critical
current density.

[0058]   The lower limit to the thickness of the
intermediate layer depends on the thickness of the CeO_2
layer, but the thickness should be at least 10 nm, with at
least 50 nm being preferable, and at least 100 nm being
even better.   If the intermediate layer is less than 10 nm
thick, then even if a CeO_2 layer is deposited on this
intermediate layer, the orientation will be over 10 degrees
and the flow of critical current will be inadequate.

<Cap Layer>

[0059]   The cap layer consists of a CeO_2 layer.   This CeO_2
layer does not need to be composed entirely of CeO_2, and
may include a Ce-M-O oxide in which part of the cerium has
been replaced with other metal atoms or metal ions.   This
CeO_2 layer can be formed by the PLD method, sputtering, or
another such method, but the use of the PLD method is
preferred because the film can be formed faster.   The
formation of the CeO_2 layer by the PLD method can be
carried out under the conditions of a substrate temperature
of approximately 500 to 800°C and a laser energy density of
1 to 5 J/cm^2, in an oxygen gas atmosphere of approximately
0.6 to 40 Pa.

[0060]   The CeO_2 layer should be at least 50 nm in
thickness, but for adequate orientation to be obtained, at

least 100 nm is preferable, and at least 500 nm is even better. However, if the thickness exceeds 500 nm, crystal orientation will suffer. Therefore, a thickness of 5000 nm or less is preferred.

<Oxide Superconducting Film>

[0061]   An RE-123-based oxide superconductor ($REBa_2Cu_3O_{7-x}$; RE is a rare earth element such as yttrium, lanthanum, neodymium, samarium, europium, or gadolinium) can be used as the material of the oxide superconducting film. The RE-123-based oxide is preferably Y123 ($YBa_2Cu_3O_{7-x}$; hereinafter referred to as YBCO) or Sm123 ($SmBa_2Cu_3O_{7-x}$; hereinafter referred to as SmBCO). The oxide superconducting film can be formed by a standard method, but the use of the TFA-MOD method or the PLD method is preferable in terms of productivity.

[0062]   Examples of the present invention will now be given along with comparative examples, but the present invention is not limited to or by these examples.

Example 1

[0063] $Gd_2Zr_2O_7$ films were deposited in various thicknesses by the IBAD method on Hastelloy metal substrates to prepare substrate samples (hereinafter referred to as IBAD substrates). A CeO_2 layers was deposited in a thickness of 500 nm by the ordinary PLD method on each IBAD substrate.

[0064]   The deposition of the CeO_2 layer by the PLD method was performed at a temperature of approximately 650°C, in an O_2 gas atmosphere of approximately 4 Pa, at a laser energy density of 3 J/cm^2, and at a laser frequency of 17 Hz. First, a CeO_2 pellet 3 cm in diameter was attached in a vacuum chamber, the inside of which was evacuated, and then the above-mentioned O_2 gas was introduced to adjust the pressure. The pellet was irradiated with a KrF excimer

laser, which resulted in a CeO_2 layer being deposited on
the IBAD substrate disposed across from the pellet. A YBCO
superconducting film was formed in a thickness of 250 nm by
the TFA-MOD method (an organometal deposition method using
trifluoroacetate, i.e., coating-pyrolysis method).

[0065]   The in-plane orientation ($\Delta\Phi$) of each sample was
examined by X-ray diffraction. Fig. 5 shows the results of
measuring the orientation of the CeO_2 layer formed in a
thickness of 500 nm on each of the IBAD-$Gd_2Zr_2O_7$ films of
various thickness. For the sake of comparison, also shown
is the orientation when there was no CeO_2 layer, that is,
the orientation of just the IBAD-$Gd_2Zr_2O_7$ layer. Fig. 5A is
a graph of the relationship between the thickness of the
IBAD film and $\Delta\Phi$, and Fig. 5B is a detail depiction of the
data for IBAD thicknesses of 100 to 1000 nm.

[0066]   It can be seen from the results shown in Fig. 5
that orientation is improved by the deposition of the CeO_2
layer. This effect is particularly pronounced when the
thickness of the IBAD layer is no more than 1000 nm. When
the CeO_2 layer was deposited in a thickness of 500 nm on
IBAD-$Gd_2Zr_2O_7$ films 1000 to 2000 nm in thickness, an
orientation of 4 degrees was obtained, which is nearly
impossible with IBAD alone. A YBCO ($YBa_2Cu_3O_{7-x}$)
superconducting layer was formed by the TFA-MOD method on
each sample, and the critical current was measured,
whereupon a high critical current density of 3 MA/cm^2 was
obtained at 77 K and 0 T.

[0067]   Fig. 6 shows the critical current density for the
various samples obtained in this experiment. As is clear
from Fig. 6, samples with better orientation exhibited
higher critical current density and were more useful for
practical application.

[0068]   Similarly, a CeO_2 oxide layer with a thickness of
500 nm was deposited on each of IBAD-$Gd_2Zr_2O_7$ layers with a

thickness of 2500 and 3000 nm. The surface roughness Ra
was measured by AFM (atomic force microscope) over a range
of 0.1 x 0.1 mm, which revealed that when the thickness is
over 2000 nm, the roughness is not less than 100 nm, which
is impractical. Specifically, the critical current density
was at least 1 MA/cm^2, just as above, when the film
thickness was not greater than 2000 nm, but when 2000 nm
was exceeded, the critical current density dropped
significantly to 0.7 MA/cm^2 because of the increase in
surface roughness shown in Fig. 6.

[0069]   On the other hand, if the thickness of the IBAD
layer is under 100 nm and a CeO_2 layer is deposited by the
PLD method, the orientation will be over 10 degrees, which
prevents adequate critical current from flowing. This is
because if the orientation is over 10 degrees, there is
insufficient electrical connection (weak bonding) between
the YBCO crystals. However, if the thickness of the IBAD
layer is at least 100 nm, the orientation of the CeO_2 layer
becomes not more than 10 degrees and sufficient current
flows. The IBAD method is a slow method, with a deposition
rate of only about 3 nm/minute, so the manufacturing time
is longer, but the deposition and manufacturing time can be
shortened by making the IBAD film thinner and forming the
CeO_2 layer thicker by the PLD method as in the present
invention.

[0070]   The results shown in Figs. 5 and 6 show that the
above-mentioned IBAD film thickness is preferably no more
than 2000 nm, the effect of which is especially pronounced
from the standpoint of increasing the manufacturing rate.
Specifically, if the IBAD layer thickness is 2000 nm or
less, the PLD-CeO_2 layer of this invention will be
effective, but the IBAD layer thickness is preferably no
more than 1000 nm, with 500 nm or less being even better.
Also, in terms of the critical current density and

orientation ultimately achieved, the thickness of the IBAD layer is preferable at least 100 nm.

Example 2

[0071]   Just as in Example 1, a $Gd_2Zr_2O_7$ film was deposited in a thickness of 500 nm by the IBAD method on a Hastelloy metal substrate to prepare a number of IBAD substrates. A CeO_2 oxide layer was deposited in various thicknesses by the PLD method. Again, the YBCO was formed by the TFA-MOD method.

[0072]   Fig. 7 shows the $\Delta\Phi$ values for various CeO_2 films formed in nine different thicknesses: 20 nm, 50 nm, 100 nm, 300 nm, 600 nm, 1000 nm, 3000 nm, 5000 nm, and 7000 nm. The smaller is the $\Delta\Phi$ value, the better the crystal orientation is, but the results shown in Fig. 7 indicate that at 7000 nm (that is, when 5000 nm is exceeded), crystal orientation is slightly worse. $\Delta\Phi$ is less than 10 degrees at a thickness between 100 and 5000 nm. A YBCO superconducting layer was formed by the TFA-MOD method onto each of these samples in the same manner as in Example 1, and the critical current was measured, which indicated Jc to be at least 1 MA/cm^2 when the CeO_2 film thickness was 50 to 7000 nm at 77 K and 0 T, and a Jc of at least 2 MA/cm^2 was obtained between 100 and 5000 nm in particular, with the highest critical current density obtained being 3 MA/cm^2.

[0073]   It can be seen from the above results that providing a CeO_2 layer in a thickness of at least 50 nm is very effective. Preferably, to achieve better orientation, this thickness should be at least 100 nm, and it can be seen that a CeO_2 layer with a thickness of at least 500 nm will afford high orientation and a sufficiently large critical current density.

[0074]   The same test was conducted using YSZ and MgO instead of $Gd_2Zr_2O_7$ as the above-mentioned IBAD intermediate layer, whereupon the results for the $\Delta\Phi$ of the CeO_2 layer and the Jc of the YBCO film were the same as before.

Example 3

[0075]   The same test as in Example 1 was conducted, except that an SmBCO ($SmBa_2Cu_3O_{7-x}$) film was formed instead of the YBCO film used as the superconducting film in Example 1, which yielded results similar to those in Example 1. Jc, however, was slightly lower than when the YBCO film was formed, and reached a maximum of only 2 MA/cm^2.

Example 4

[0076]   The same test as in Example 1 was conducted, except that an NdBCO ($NdBa_2Cu_3O_{7-x}$) film was formed instead of the YBCO film used as the superconducting film in Example 1, which yielded results similar to those in Example 1. Jc, however, was slightly lower than when the YBCO film was formed, and reached a maximum of only 2 MA/cm^2.

Example 5

[0077]   The same test as in Example 1 was conducted, except that the thickness of the CeO_2 layer used in Example 1 was changed to 5000 nm. As a result, similarly to Example 1, orientation increased when the CeO_2 layer was deposited. This effect was particularly pronounced when the thickness of the IBAD layer was 1000 nm or less. When the CeO_2 layer was deposited in a thickness of 5000 nm on each of IBAD-$Gd_2Zr_2O_7$ films 1000 to 2000 nm in thickness, an orientation of 4 degrees ($\Delta\Phi$) was obtained, which is nearly impossible with IBAD alone. A YBCO superconducting layer

was formed by the TFA-MOD method onto each of these samples, and the critical current was measured, whereupon a maximum critical current density of approximately 3 MA/cm^2 was obtained at 77 K and 0 T. As in Example 1, these results indicate that samples with better orientation exhibited higher critical current density and were more useful for practical application.

Example 6
[0078] The same test as in Example 1 was conducted, except that stainless steel and a nickel alloy were used instead of the Hastelloy used as the metal substrate in Example 1. Here again, the results for the $\Delta\Phi$ of the CeO_2 layer and the Jc of the YBCO film were the same as before.

Example 7
[0079] The same test as in Example 1 was conducted, except that the method for manufacturing the YBCO film was changed from the TFA-MOD method to the PLD method, whereupon the results for the $\Delta\Phi$ of the CeO_2 layer and the Jc of the YBCO film were the same as in Example 1.

Example 8
[0080] A CeO_2 layer with a thickness of 500 nm was formed by the PLD method on the IBAD substrate used in Example 1 ($Gd_2Zr_2O_7$ film thickness: 300 nm), such that the film formation rate, based on thickness, was 0.5 to 10,000 nm/minute. Fig. 8 is a graph of the results of measuring the surface roughness (Ra) of the CeO_2 layer obtained at various film formation rates.
[0081] Film formation rates of 0.5 and 10,000 nm/minute were impractical because of the large Ra value. On the other hand, Ra was 20 nm or less between 1 and 5000 nm/minute, with the surface in good condition. A YBCO

film was formed on each of these samples by the TFA-MOD
method in the same manner as in Example 1, and the critical
current was measured, which indicated Jc to be at least 1.5
MA/cm^2 at 77 K and 0 T when the CeO$_2$ layer was formed at a
rate of 1 to 5000 nm/minute. Jc was 3 MA/cm^2 with a YBCO
film on a CeO$_2$ layer formed at 10 nm/minute.

[0082]   The present invention is characterized in that the
film formation rate is markedly higher than with a
conventional IBAD film formation method. Specifically, if
the IBAD film formation rate is 3 nm/minute and the CeO$_2$
layer formation rate is 50 nm/minute, when the CeO$_2$ layer
is formed in a thickness of 100 nm on the IBAD film with a
thickness of 2000 nm by a conventional method, the total
time required is 668 minutes (2000 (nm) ÷ 3 (nm/minute) +
100 (nm) ÷ 50 (nm/minute) = 668 minutes). In contrast,
with the present invention, when a CeO$_2$ layer of 500 nm is
formed on an IBAD film of 300 nm, the total time required
is 110 minutes (300 (nm) ÷ 3 (nm/minute) + 500 (nm) ÷ 50
(nm/minute) = 110 minutes).

[0083]   As discussed above, the oxide superconducting wire
of the present invention can be manufactured in less time
than with a conventional method, and has the further
advantage that its orientation will be the same as or
better than a conventional wire, as shown in Figs. 5 and 7.

Example 9

[0084]   A CeO$_2$ layer was formed at a laser energy density
of 0.7 to 6 J/cm^2 by the PLD method on the IBAD substrate
used in Example 1 (Gd$_2$Zr$_2$O$_7$ film thickness: 300 nm). The
CeO$_2$ layer thickness was 500 nm. Fig. 9 is a graph of the
results of measuring the crystal orientation ΔΦ at various
laser energy densities. Levels of 0.7 and 6 J/cm^2 were
impractical for the reason given in Example 1, since ΔΦ was

over 10 degrees in these cases.   ΔΦ was not more than 10 degrees between 1 and 5 J/cm^2.

[0085]   A YBCO superconducting layer was formed on each of these samples by the TFA-MOD method in the same manner as in Example 1, and the critical current was measured, which indicated Jc to be at least 1 MA/cm^2 at 77 K and 0 T on a CeO$_2$ layer formed at 1 to 5 J/cm^2.   In particular, with a YBCO film on a CeO$_2$ layer formed at 1.5 to 4 J/cm^2, Jc was at least 2 MA/cm^2, and the maximum Jc was 3 MA/cm^2 with a YBCO film on a CeO$_2$ layer formed at 1.5 J/cm^2, just as in Example 1.

[0086]   The present invention allows the IBAD film of the intermediate layer to be made thinner, so the IBAD method takes less time and the productivity of superconducting wire is higher.   Also, increasing the thickness of the CeO$_2$ layer provided as the cap layer reduces the surface roughness of the CeO$_2$ layer and affords a surface of higher orientation, so when an oxide superconducting film is formed on this surface, a superconducting film of higher critical current density can be obtained.